

## Product Information



بازرگانی پیلار  
واردات و فروش مستقیم مواد شیمیایی  
تلفن ۰۲۱۷۷۹۰۰۷۳۳

# BERMOCOLL<sup>®</sup> EBS 481FQ

BERMOCOLL EBS 481 FQ is a non-ionic, water soluble cellulose ether with enhanced enzyme resistance. It improves the consistency, the stability, and the water retention of water based products.

### Specifications

BERMOCOLL EBS 481 FQ is a high viscosity grade of ethyl hydroxyethyl cellulose.

### Physical data

Appearance	whitish powder
Particle size	98 % < 500 µm
Water content	max 4 %
Salt content	max 5 %

### Characteristics of aqueous solutions

pH (1 % solution)	5-7
Surface activity	weak
Viscosity at 20°C (Brookfield LV) 1 % solution	4 000 – 6 000 mPa·s

### Applications

BERMOCOLL EBS 481 FQ is used in latex paints for thickening and stabilizing effects, particularly when high storage viscosity combined with low application viscosity is required. Normal dosage is 0.2 - 0.7 % calculated on the total paint weight. BERMOCOLL EBS 481 FQ is easily dispersed in cold water of pH 7 or less.

BERMOCOLL EBS 481 FQ can form lumps when added to an alkaline liquid. To avoid this, it should be added as a ready stock solution, as a slurry in slight acid water or in an organic solvent, or as a dry mix with other powder materials.

The dissolving time after dispersion is influenced by the water pH. Alkaline additives can be used to speed up the dissolving process.

### Safety instructions, Packaging and Storage

Like many industrial processed powdery materials, cellulose ether dusts are combustible and can cause dust explosions. Dust formation must be avoided or kept to a minimum. Care should be taken to prevent ignition from heat, spark, open flames or hot surface.

BERMOCOLL EBS 481 FQ is packed in Polyethylene bags. Net weight 20 kg. We recommend emptying the bags from the bottom. The empty bags can be recycled or burned. In unopened bags, BERMOCOLL EBS 481 FQ can be stored for several years. In opened bags, the moisture content of BERMOCOLL EBS 481 FQ will be influenced by the air humidity.

At the temperatures above 250°C (480°F), charring of BERMOCOLL EBS 481 FQ will occur. At high temperatures and in contact with an open flame, BERMOCOLL EBS 481 FQ will burn slowly with the characteristics of cellulose.

CCD 3314

