

# SODASIL P 95

Amorphous aluminium silicate with a high degree of whiteness

n° CAS 1344-00-9  
n° EINECS 215-684-8

## NATURE

Amorphous aluminium and sodium silicate obtained by precipitation in an aqueous medium.

## TECHNICAL DATA

	Mean values
BET specific surface area (m <sup>2</sup> /g)	70
Particle size (µm)	6
Tamped density (g/l)	250
Loss on drying (%)	6
Loss on ignition (%)	14
Conductivity, 10% water suspension (mS/cm)	<1
DBP absorption (ml/100g)	160
pH, 5% water suspension	10.5
Chemical composition of ignited product (%)	
SiO <sub>2</sub>	82
Al as Al <sub>2</sub> O <sub>3</sub>	9.5
Na as Na <sub>2</sub> O	8.1

## PROPERTIES

- Homogeneous particle size.
- High degree of whiteness.
- Easily dispersible in rubber, plastic, in liquid and powder products.



بازرگانی پیلار  
واردات و فروش مستقیم مواد شیمیایی  
تلفن ۰۲۱۷۷۹۰۰۷۳۳

### ■ FIELDS OF APPLICATION

- Production of decorative paints and emulsion paints:
  - Partial substitution of  $\text{TiO}_2$
  - Matting agents in semigloss systems
- Paper production:
  - As an extender of  $\text{TiO}_2$
  - As a white pigment for newsprint paper, coated paper,...
- Filler in printing inks.
- Fluidizing and anti-caking agent.

### ■ SAFETY CLASSIFICATION FOR STORAGE AND TRANSPORT

It is not classified as a dangerous substance according to EEC Directives on "Classification, packaging and labelling of dangerous substances".

### ■ STORAGE

Store in a dry place to maintain the product's physical properties.

It should not be stored for longer than one year from the supply date.

### ■ CONTAINERS

- 25 kg sacks.
- Big bags.
- Silo truck.

G R U P O