www.PilarTejarat.Com

LDPE LLDPE MDPE HDPE PP PVC GPPC HIPS EPS PET ABS SBR PBR PC E.P.





)) Product Description:

PVC EVY 12 is a fine-particle emulsion homopolymer for making PVC pastes. Plastisols based on PVC EVY 12 are distinguished by a low initial viscosity and almost newtonian flow properties.

Y) Applications:

Principal applications are pastes for compact vinyl wall coverings, flooring and leather cloth, as well as for coating of woven and non-woven fabrics and of glass strands.

") Typical Data

| Row material properties | Unit | Test method | | T* |
|--|------|---|---------------|----------------|
| | | DIN | ISO | Typical value* |
| K-Value | | ٥٣٧٢٦ | ۱٦٢٨/٢ | V1-VT |
| Particle size distribution: sieve retention retained on Tr mm screen | % | 0414 | 070 | <1.0 |
| Volatile matter | % | ٧٧٦٤/٢ | ١٢٦٩ | <.٣ |
| Methanol extract | % | ٥٣٧٣٨ | 7 £ 7 7 | <٢.٥ |
| theromostability: | min | Vinnolit THMA ۱۸۰ | | >٢٠ |
| Past viscosity after \ h | pas | DIN EN 1127A DIN EN TY19 PVC/DOP=1/1. YT c, 17SEC | ISO 1 1 £ A A | <° |
| Residual VCM | ppm | 07787 | 7(2.1 | <1 |

^{*}The values given above are **typical** test results which should be used as a guide only. The do not form the whole or part of a specification or guarantee.

(1) Processing

On account of its favorable rheology at high shear rates, pastes made from PVC E^{YY} is can be processed with all the usual coating methods, particularly with reverse roll coaters. The following properties make PVC E^{YY} is particularly suited to the manufacture of low plasticizer and/or highly filled pastes:

- Very low initial viscosity
- Almost linear flow properties
- Excellent release effect during contact fusion
- High suitability for mechanically blown foam containing silicone based foaming aids