



بازرگانی پیلار
واردات و فروش مستقیم مواد شیمیایی
تلفن ۰۲۱۷۷۹۰۰۷۳۳

LG PVC PB1302

Paste PVC

Introduction

PB1302, homopolymer made from micro- suspension polymerization, is a low- viscosity PVC resin with a pseudo plastic flow property in processing range.

PB1302 can be used for casting leather sheet, sheets made by Knife coating/ roll coating

Application

General purpose grade for flooring, fabric coating

Properties

| Item | Test Method | Unit | Test Condition | Value |
|-------------------------------------|---------------|-------------------|----------------|-------------|
| Degree of Polymerization | JIS K 6721-77 | - | 30°C | 1250 ± 100 |
| K-Value | DIN 53726 | - | - | 71 |
| Apparent Bulk Density | ASTM D1895-90 | g/cm ² | - | 0.36 ± 0.06 |
| Volatiles | ASTM D3030-90 | % | 110°C x 1hr | Max 0.2 |
| Brookfield Viscosity (DOP 60phr) | ASTM D1824-90 | cps | 6 RPM | - |
| Sever Viscosity(DOP 60phr) | ASTM D3030-90 | g/sec | 4 BAR | Min 0.4 |

*Note : 1)The values of properties in the above table have been obtained by the test pieces(natural color) manufactured under certain of injection.

2)The listed values should be used for referential purposed only.

Test Condition

1) Brookfield Viscosity

Fomulation Resin 100, DOP refer to chart
Condition
Rotational Viscometer
Mode LVT Type, Rotor RPM 6, 12

2) Severs Viscosity

Condition
Severs Extrusion Rheometer
Orifice diameter 3.043mm, length 50mm
Pressure 4, 8 Bars

Contact the technical team of PVC & Plasticizer any questions or requirements relevant to PB1302 products.



Tech center, 84, Jang-dong, Yusung-gu, Taejon, Korea

Tel: 82-42-860-8511, Fax : 82-42-863-2385